



KENT ATEŞ TUĞLA REFRAKTER

LOW CEMENT CASTABLE

Brand Name	Chemical Analysis				Density kg/cm ³	Application Temperature °C	Grain Size mm
	%						
	Al ₂ O ₃	Fe ₂ O ₃	SiO ₂	CaO			
KENT LOW CAST 50	50	1,0	45	2	2,35	1500	0 - 5
KENT LOW CAST 60	60	1,0	35	1,8	2,40	1600	0 - 5
KENT LOW CAST 65	65	0,8	30	1,8	2,70	1650	0 - 5
KENT LOW CAST 75	75	1,0	20	1,9	2,60	1650	0 - 5
KENT LOW CAST 85	85	1,0	8	2	2,65	1650	0 - 5
KENT LOW CAST 95	95	0,1	2,8	1,75	3,00	1650	0 - 5

INSULATION CASTABLE

Brand Name	Chemical Analysis				Density kg/cm ³	Application Temperature °C	Grain Size mm
	%						
	Al ₂ O ₃	Fe ₂ O ₃	SiO ₂	CaO			
KENT İSO CAST 650	26	3,5	30	35	0,5	650	0 - 5
KENT İSO CAST 800	28	3,0	30	30	0,6	800	0 - 5
KENT İSO CAST 950	30	3,5	35	24	0,6	950	0 - 5
KENT İSO CAST 1000	20	5,0	30	34	0,75	1000	0 - 5
KENT İSO CAST 1100	33	3,0	35	25	0,65	1100	0 - 5
KENT İSO CAST 1250	38	3,0	36	17	1,0	1250	0 - 5
KENT İSO CAST 1350	45	2,0	35	12	1,3	1350	0 - 5
KENT İSO CAST 1400	60	0,6	24	10	1	1400	0 - 5

The above technical information represents average values. These data serves to give general information. They are not guarenteed specifications.

